

CoolTherm™ EP-6037 Epoxy Resin

Description

LORD CoolTherm™ EP-6037 epoxy resin is formulated for use with various CoolTherm hardeners to create a two-component epoxy system. The epoxy system is primarily used by the semiconductor industry to form thermally conductive joints in fabricated heat sinks and between heat sinks and power devices. CoolTherm EP-6037 resin can also be mixed with CoolTherm hardeners for bonding semiconductors and transistors to heat sinks, and for general purpose bonding of electronic components.

Features and Benefits

Low Stress – exhibits low shrinkage and stress on components as it cures.

Excellent Adhesion – provides a strong adhesion bond to a wide variety of substrates.

Low Coefficient of Thermal Expansion – minimizes the possibility of cracking during severe temperature cycling.

Application

Mixing – Thoroughly stir CoolTherm EP-6037 resin within its shipping container to ensure uniform dispersion. Transfer amount of resin needed to a clean container and add proper amount of hardener by weight.

Thoroughly mix epoxy system using an air-driven mixer. Be careful not to whip excessive air into the epoxy.

Applying – To ensure a void-free bondline, evacuate epoxy for 5 minutes before application. Apply epoxy to both mating surfaces and press together, squeezing out excess epoxy to obtain a thin bondline. Clamp in position to prevent movement during epoxy cure.

Curing – Cure time will vary depending on hardener used. Refer to cure schedules indicated below. Time-at-temperature profiles refer to the time the bondline should be allowed to cure once it reaches the target temperature. Allowance should be made for oven ramp rates, parts with large thermal mass and other circumstances that may delay bondline reaching the target temperature.

Typical Properties* of Resin Mixed with Hardener

	CoolTherm EP-6010 Hardener	CoolTherm EP-6252 Hardener
Mix Ratio, by Weight Resin to Hardener	100:3.4	100:7.1
Working Life, hr @ 25°C	2	3
Cure Time, hr @ 25°C	24	24
@ 65°C	2	2

*Data is typical and not to be used for specification purposes.

Typical Properties*

Appearance	Black or Green Paste
Viscosity, cps @ 25°C	500,000
Specific Gravity	2.35

*Data is typical and not to be used for specification purposes.

LORD TECHNICAL DATA

Shelf Life/Storage

Shelf life is one year from date of manufacture when stored at 25°C in original, unopened container.

Cautionary Information

Before using this or any LORD product, refer to the Safety Data Sheet (SDS) and label for safe use and handling instructions.

For industrial/commercial use only. Must be applied by trained personnel only. Not to be used in household applications. Not for consumer use.

Typical Cured Properties*

	CoolTherm EP-6010 Hardener	CoolTherm EP-6252 Hardener
Volume Resistivity, ohm-cm @ 25°C	>1 x10 ¹⁵	>1 x10 ¹⁵
Thermal Conductivity, W/mk	1.2	1.1
Coefficient of Linear Thermal Expansion, ppm/°C	52	31
Glass Transition Temperature (Tg), °C by TMA	106	70
Hardness Shore D	93	92
Tensile Strength, psi @ 25°C	7250	8700
Lap Shear Strength, psi @ 25°C Aluminum to aluminum, 1" overlap	1450	2175
Elongation at Break, %	1.9	4.1
Moisture Absorption, % 10 days @ 25°C	0.076	0.17
Dielectric Strength, V/mil	> 400	> 400

*Data is typical and not to be used for specification purposes.

Values stated in this technical data sheet represent typical values as not all tests are run on each lot of material produced. For formalized product specifications for specific product end uses, contact the Customer Support Center.

Information provided herein is based upon tests believed to be reliable. In as much as LORD Corporation has no control over the manner in which others may use this information, it does not guarantee the results to be obtained. In addition, LORD Corporation does not guarantee the performance of the product or the results obtained from the use of the product or this information where the product has been repackaged by any third party, including but not limited to any product end-user. Nor does the company make any express or implied warranty of merchantability or fitness for a particular purpose concerning the effects or results of such use.

CoolTherm and "Ask Us How" are trademarks of LORD Corporation or one of its subsidiaries.

LORD provides valuable expertise in adhesives and coatings, vibration and motion control, and magnetically responsive technologies. Our people work in collaboration with our customers to help them increase the value of their products. Innovative and responsive in an ever-changing marketplace, we are focused on providing solutions for our customers worldwide ... Ask Us How.

LORD Corporation World Headquarters

111 Lord Drive
Cary, NC 27511-7923
USA

www.lord.com

For a listing of our worldwide locations, visit LORD.com.

LORD
AskUsHow™