

CoolTherm® SC-6703 Thermally Conductive Silicone Encapsulant

Description

LORD CoolTherm® SC-6703 thermally conductive silicone encapsulant is a two-component system designed to provide thermal conductivity for encapsulating densely packed power units.

Features and Benefits

Low Stress – exhibits low shrinkage and stress on components as it cures.

Environmentally Resistant – provides excellent thermal shock resistance.

UL Rated – meets requirements of UL 94 V-O standard; provides excellent flame retardancy.

Application

Mixing – Thoroughly mix each component prior to combining resin and hardener. Mix CoolTherm SC-6703 resin with CoolTherm SC-6703 hardener at a 1:1 ratio, by weight. Automatic meter/mix/dispense equipment may be used for high volume production.

Unless a closed-chamber mechanical mixer is used, air may be introduced into the encapsulant system either during mixing or when catalyzing the mixture. Electrical properties of the silicone encapsulant are best when air bubbles and voids are minimized. Therefore, in extremely high voltage or other critical applications, vacuuming may be appropriate.

Applying – Apply silicone encapsulant using handheld cartridges or automatic meter/mix/dispense equipment.

Avoid applying CoolTherm SC-6703 encapsulant to surfaces that contain cure inhibiting ingredients, such as amines, sulfur, or tin salts. If bonding surface is in question, apply a test patch of CoolTherm SC-6703 encapsulant to the surface and allow it to set for the normal cure time.

Curing – Allow encapsulant to cure for 4 hours at 65°C. This time-at-temperature profile refers to the time the bondline should be allowed to cure once it reaches the target temperature. Allowance should be made for oven ramp rates, parts with large thermal mass and other circumstances that may delay bondline reaching the target temperature.

Typical Properties*

	SC-6703 Resin	SC-6703 Hardener	Mixed
Appearance	Black Liquid	White Liquid	Light Gray Liquid
Viscosity, cps @ 25°C	15,000	6000	8000
Specific Gravity	2.09	1.91	2.0
Gel Time, min @ 66°C	–	–	12-14
Working Life, hr @ 25°C	–	–	1-2

*Data is typical and not to be used for specification purposes.

LORD TECHNICAL DATA

Typical Cured Properties**

Volume Resistivity, ohm-cm @ 25°C ASTM D 257	1 x 10 ¹⁴
Thermal Conductivity, W/m·K Hot Disc Transient Method	0.8
Coefficient of Linear Thermal Expansion, ppm/°C ASTM C 864	220
Hardness Shore A	60
Tensile Strength, MPa (psi) ASTM D 412	1.38 (200)
Elongation at Break, % ASTM D 412	80
Dielectric Strength, kV/mm (V/mil)	19.7 (500)
Dielectric Constant @ 25°C 1 MHz, ASTM D 150	4.25
Dissipation Factor, % @ 25°C 1 MHz, ASTM D 150	0.02

**Data is typical and not to be used for specification purposes.
Cure schedule of 1-2 hours at 65°C.

Shelf Life/Storage

Shelf life of each component is six months from date of manufacture when stored at 25°C in original, unopened container. The material must be periodically rotated within its container to maintain maximum shelf life. Settling will occur if not mixed.

Cautionary Information

Before using this or any LORD product, refer to the Safety Data Sheet (SDS) and label for safe use and handling instructions.

For industrial/commercial use only. Must be applied by trained personnel only. Not to be used in household applications. Not for consumer use.

Values stated in this technical data sheet represent typical values as not all tests are run on each lot of material produced. For formalized product specifications for specific product end uses, contact the Customer Support Center.

Information provided herein is based upon tests believed to be reliable. In as much as LORD Corporation has no control over the manner in which others may use this information, it does not guarantee the results to be obtained. In addition, LORD Corporation does not guarantee the performance of the product or the results obtained from the use of the product or this information where the product has been repackaged by any third party, including but not limited to any product end-user. Nor does the company make any express or implied warranty of merchantability or fitness for a particular purpose concerning the effects or results of such use.

CoolTherm is a trademark of LORD Corporation or one of its subsidiaries.

LORD provides valuable expertise in adhesives and coatings, vibration and motion control, and magnetically responsive technologies. Our people work in collaboration with our customers to help them increase the value of their products. Innovative and responsive in an ever-changing marketplace, we are focused on providing solutions for our customers worldwide.

LORD Corporation World Headquarters

111 Lord Drive
Cary, NC 27511-7923
USA

www.lord.com

For a listing of our worldwide locations, visit LORD.com.