

# Sipiol® WL 1026-21 Coating

## Description

LORD Sipiol® WL 1026-21 coating is an aqueous, single-component, anti-friction coating designed for in-line application during production of automotive sealing systems. Sipiol WL 1026-21 coating is a high abrasion-resistant coating with a micro-structured surface.

## Features and Benefits

**Abrasion Resistant** – provides excellent abrasion resistance against rotating textile.

**Durable** – provides excellent chemical resistance and high elasticity.

**Low Coefficient of Friction** – provides a low coefficient of friction coating with improved glass drag properties and non-stick to glass.

**Versatile** – when used in combination with thickener, suitable for off-line application.

**Noise Reduction** – reduces noise generated when surface is in contact with coated metals and glass.

Abrasion Resistant	Chemically Resistant	Low Coefficient of Friction	Noise Vibration	Weathering
+++	+++	+++	+++	++++

## Application

**Surface Preparation** – Remove contaminants from surface. Prime substrate with Sipiol WP 8555 or Cuvertin® X 8536 primer. Alternative surface preparation, such as plasma treatment, is recommended for improved adhesion to low polarity substrates.

**Mixing** – Thoroughly stir Sipiol WL 1026-21 coating prior to application using an electric stirrer at low speed. If a lower viscosity is required, dilute coating with deionized water, up to 30 parts of water to 100 parts of coating. If a higher viscosity is required, add up to 2% Sipiol TH1 additive. Before use, filter coating using a sieve with pore size of 190-260 µm.

If coating is spray applied, equip spray container with built-in stirrer to prevent sedimentation.

**Applying** – Apply Sipiol WL 1026-21 coating by HVLP spray methods at temperatures above 10°C (50°F). Coating can be applied up to a maximum substrate temperature of 120°C (248°F).

For optimum performance, dry film thickness of Sipiol WL 1026-21 coating should be 8-20 micron (0.3-0.8 mil).

## Typical Properties\*

Appearance	Black Liquid
Viscosity, cps @ 25°C (77°F) Brookfield LVT Spindle 1, 30 rpm	50-150
Density @ 20°C (68°F) g/cm <sup>3</sup> (lb/gal)	1.00-1.10 (8.35-9.18)
Solids Content by Weight, % 2.5 gram dried 30 min @ 130°C (266°F)	36-40

\*Data is typical and not to be used for specification purposes.

# LORD TECHNICAL DATA

**Drying/Curing** – Cure coating at 130-200°C (266-392°F), with dwell time depending on line speed and oven length. Typically, 1-2 minutes at 180°C (356°F) surface temperature is sufficient.

**Cleanup** – Use water to clean up equipment.

## Shelf Life/Storage

Shelf life is one year from date of manufacture when stored in a non-corrosive environment below 20°C (68°F) in original, unopened container. Do not store near direct heat sources. Keep container tightly sealed when not in use to prevent skinning. Do not freeze product.

## Cautionary Information

Before using this or any LORD product, refer to the Safety Data Sheet (SDS) and label for safe use and handling instructions.

*For industrial/commercial use only.* Must be applied by trained personnel only. Not to be used in household applications. Not for consumer use.

Values stated in this technical data sheet represent typical values as not all tests are run on each lot of material produced. For formalized product specifications for specific product end uses, contact the Customer Support Center.

Information provided herein is based upon tests believed to be reliable. In as much as LORD Corporation has no control over the manner in which others may use this information, it does not guarantee the results to be obtained. In addition, LORD Corporation does not guarantee the performance of the product or the results obtained from the use of the product or this information where the product has been repackaged by any third party, including but not limited to any product end-user. Nor does the company make any express or implied warranty of merchantability or fitness for a particular purpose concerning the effects or results of such use.

Sipiol, Cuvertin and "Ask Us How" are trademarks of LORD Corporation or one of its subsidiaries.

LORD provides valuable expertise in adhesives and coatings, vibration and motion control, and magnetically responsive technologies. Our people work in collaboration with our customers to help them increase the value of their products. Innovative and responsive in an ever-changing marketplace, we are focused on providing solutions for our customers worldwide ... Ask Us How.

**LORD Corporation**  
**World Headquarters**  
111 Lord Drive  
Cary, NC 27511-7923  
USA

**Europe**  
2, Chemin du Pavillon  
CH-1218 Le Grand Saconnex  
Geneva, Switzerland  
+41 (0) 22 761 50 60

[www.lord.com](http://www.lord.com)

For a listing of our worldwide locations, visit [LORD.com](http://LORD.com).

**LORD**  
AskUsHow™